



WATERBASED URETHANE

2-COMPONENT, 2 TO 1 MIX RATIO



epoxyplus
Epoxy coatings plus a whole lot more.

PRODUCT DATA

Volumetric Ratio	2 to 1
Solids Content	42%
Coverage	350 -400 SF/gal.
Pot Life	1 hour
Pot Life is reduced by increasing temperature and/or mass.	
Cure times	(70 degrees,
Dry to Touch	7 - 9 hours
Recoat	8 -12 hours
Light Traffic	24 hours
Full Cure	3 -5 days
Higher Temp & Lower humidity will accelerate cure times.	
Lower temp & higher humidity will lengthen cure time.	
VOC	306g/l
Performance Properties	
Gloss, Clear	>70 at 60 degrees
Pendulum hardness	182
Tabor Abrasion-1000gm.Load	
1000 cycles, CS17 Wheel	21mg.loss
Colors	Clear
Finish	Gloss
Packaging 1.5 Gallon Kit:	
Part A	128 oz
Part B	64 oz

SURFACE PREPARATION

Prepare surface by sanding, grinding, dry or wet sandblasting or shot blasting to achieve a clean, porous and uniform surface that will allow the product to penetrate the surface. Bead or shotblasting is the most reliable method of preparation. All surfaces must be dry prior to application. For application over epoxy coatings, EP-U1000 must be installed within 24 hours of previous coating. If this window of time is missed, sanding is required.

MILDEW

DO NOT PAINT OVER MILDEW. Mildew is a fungus, brown, black, gray or even white in color, and will rapidly grow through any coating applied over it. A solution of 50% household bleach and 50% water will kill the mildew. See precautions on bleach label for handling before using.

PRODUCT DESCRIPTION

A premium high solids 2-component aliphatic water base urethane. Epoxy Plus Waterbased Urethane (WBU) is VOC compliant in California. It is a hard, durable coatings that features good gloss, superior abrasion resistance and UV resistance. Epoxy Plus WBU has been formulated to offer a high performance finish coat for seamless flooring, coatings and architectural concrete applications where odor and health concern are sensitive.

Typical areas of application are clean rooms, hospitals, grocery stores, walkways, garage floor, parking structure, aircraft hangers and automotive repair facilities.

ADVANTAGES

Unsurpassed adhesion. Easy clean-up. Good pot life (1 hour). Excellent coverage-hide.

INSPECTION

Surface must be structurally sound, dry, and free of oil, grease, curing agents, dirt, dust or other foreign matter. Surface must be roughed up or porous.

This product is designed for use over untreated concrete surfaces free from wax, dusting preventive sealers, deep penetrating sealers, bond breaking compounds and release agents and other similar chemicals that will interfere with proper adhesion and lead to premature coating failures.

MIXING

MIX 2 PARTS "A" WITH 1 PART "B" IN BATCHES NO LARGER THAN 1.5 GALLONS AT A TIME EXCEPT AS NOTED ABOVE UNDER "SELF PRIMING REQUIREMENTS".

Top Coat: In a clean and dry bucket, mix 2 parts A and 1 part B together using an agitator, jiffy mixer or similar.

Mix slowly for at least 2 minutes or until completely combined. Prepare only the amount you can use in 1 hours at 74F. (Higher temperatures reduce work time).

Do not leave the mixed material in the bucket longer than 1 hours.



TECHNICAL DATA SHEET

125 Broad Ave, Unit 13 North Bergen, NJ 07047
1 (888) 361-2641 WWW.EPOXYPLUS.COM



epoxyplus
Epoxy coatings plus a whole lot more.

APPLICATION INSTRUCTIONS

Use a 3/8" nap roller. Dip and roll at the recommended coverage rate. Keep a wet edge. Direct sunlight and high temperatures can cause roller marks. Too thick of an application can cause solvent entrapment and product failure. Clean tools with soap and water before curing begins. To increase skid resistance, stir in an approved non-skid additive into your A & B mixture.

FILM THICKNESS

Three (3) mil to five (5) mil wet film thickness

THINNING

Not recommended.

CONCRETE SURFACE PREPARATION

Concrete surfaces should be clean, dry, and free of disintegrating chalky material or previously applied coatings to insure satisfactory results. To increase adhesion, dense or machine trowelled concrete surfaces should be prepared mechanically as described in surface preparation or etched with a solution of one part muriatic acid and two-parts clean water. The surface profile should resemble 80 grit sandpaper to be suitable for coating. Neutralize the surface by applying a mixture of 1 lb. baking soda mixed into 1 gal of water and rinse thoroughly. Clean all surfaces with T.S.P. and rinse with clean water.

DRYING TIME/CURE TIMES

Under normal Conditions (70°F & 50% Humidity) dries to touch in 7 to 9 hours. Do not apply to surfaces when ambient or surface temperatures are below 50°F. Higher temperatures and lower humidity will accelerate cure times and reduce working time.

WARNING! SLIP AND FALL PRECAUTIONS

OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slipresistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. Epoxy PlusFlooring recommends the use of angular slipresistant aggregate in all floorcovering systems that may be exposed to wet, oily or greasy conditions. It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. Epoxy Plus or its sales agents will not be responsible for injury incurred in a slip and fall accident.



TECHNICAL DATA SHEET

125 Broad Ave. Unit 13 North Bergen, NJ 07047
1 (888) 361-2641 WWW.EPOXYPLUS.COM



Handling Precautions

Use only with adequate ventilation. Appropriate cartridge-type respirator must be used during application in confined areas. Avoid contact with skin. Some individuals may be allergic to epoxy resin. Protective gloves and clothing are recommended.

WARRANTY

Epoxy Plus products are warranted for one year after date of purchase. Please refer to the Limited Material warranty for additional clarification.

KEEP OUT OF REACH OF CHILDREN

NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications.

NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT. We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may CAUSE SERIOUS PHYSICAL INJURY.

BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.